



Typar® SF Geotextile

Technical Data Sheet International


Property	Standard	Unit	SF20	SF24	SF27	SF32	SF33	SF37	SF40	SF44	SF45	SF49	SF56	SF65	SF77	SF85	SF95	
Descriptive properties																		
Area weight	EN ISO 9864	g/m ²	68	80	90	110	110	125	136	150	150	165	190	220	260	290	320	
Thickness under 2kN/m ²	EN ISO 9863-1	mm	0.35	0.38	0.39	0.43	0.45	0.45	0.47	0.48	0.50	0.49	0.57	0.59	0.65	0.73	0.74	
Thickness under 200kN/m ²	EN ISO 9863-1	mm	0.28	0.29	0.31	0.35	0.36	0.37	0.39	0.40	0.40	0.40	0.48	0.53	0.59	0.69	0.69	
Mechanical properties																		
Energy absorption	EN ISO 10319	kJ/m ²	1.0	2.0	1.8	3.0	3.2	3.6	3.7	4.5	4.8	5.8	5.8	7.4	8.6	9.8	11.4	
Tensile strength	ASTM D4595	kN/m	3.4	5.0	5.0	7.0	8.0	8.5	9.0	10.3	12.0	12.6	13.1	16.5	20.0	21.3	25.0	
Elongation	ASTM D4595	%	35	40	40	45	42	52	52	52	50	52	52	55	55	55	55	
Tensile strength at 5%	ASTM D4595	kN/m	1.8	2.3	2.6	3.3	3.0	3.5	3.8	4.2	4.4	5.2	5.5	6.4	7.8	8.2	9.2	
Puncture strength	ASTM D6241	N	500	700	750	1000	1100	1200	1250	1575	1600	1800	1850	2350	2900	3150	3500	
Tear strength	ASTM D4533	N	160	200	215	280	260	320	370	370	320	335	420	410	430	600	480	
Puncture "US Rod"	ASTM D4833	N	120	180	160	200	200	230	250	290	280	320	370	440	500	570	630	
Dynamic cone puncture	EN ISO 13433	mm	50	45	45	35	35	33	29	27	30	30	22	25	22	16	17	
Hydraulic properties																		
Opening size O ₉₀ wet	EN ISO 12956	µm	225	210	175	140	200	130	120	100	130	90	80	80	75	70	70	
Opening size O ₉₅ dry	ASTM D4751	µm US Sieve	550 30	490 40	350 40	300 60	460 40	220 70	210 70	200 70	250 60	120 120	100 140	80 200	<75 >200	<75 >200	<75 >200	
Permittivity	ASTM D4491	1/s	3.04	2.1	2.00	1.85	1.3	1.20	1.20	1.10	0.8	0.56	0.65	0.45	0.35	0.40	0.30	
Permeability ViH50	EN ISO 11058	10 ⁻³ m/s	180	110	100	70	65	50	50	40	33	25	35	18	12	15	5	
Flow rate at 10cm WH	BS 6906-3	l/(m ² .s)	240	190	175	110	113	80	75	70	68	50	60	35	23	30	15	
Permeability at 20kN/m ²	DIN 60500-4	10 ⁻⁴ m/s	5.2	4.9	4.7	4.6	3.5	3.2	2.8	2.6	2.6	1.7	1.9	1.6	1.4	1.6	1.1	
Permeability at 200kN/m ²	DIN 60500-4	10 ⁻⁴ m/s	3.2	3.1	3.1	2.9	2.3	1.8	2.0	1.8	1.7	1.2	1.4	1.2	1.0	1.2	0.8	
Durability																		
Predicted to be durable for a minimum of 100 years in all natural soils.																		
Natural UV light	Good resistance up to several months in direct sunlight, but prolonged exposure, particularly in tropical sunlight, can cause strength losses. Product should be covered after 2 weeks of installation.																	
Moisture	Does not absorb moisture																	
Rot, Mildew	Unaffected																	
Natural occurring acids and alkali	Unaffected																	
Oxydation Resistance EN ISO 13438	100% retained strength																	
Chemical Resistance EN 14030	100% retained strength																	
Microbiological Resistance EN 12225	100% retained strength																	
Product Description																		
Polymer	100% Polypropylene. UV stabilized																	
Specific gravity	0.91																	
Melting point	165°C																	
Type of fibre	Continuous filament																	
Fibre diameter	40/60 µm																	
Fibre bonding	Thermal bonding																	
Color	Grey																	
<p><i>The values correspond to average results obtained in our laboratories and outside institutes and are indicative.</i></p> <p><i>The right is reserved to make changes at any time without notice.</i></p>																		

Further product information is available upon request. This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own testing. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

DuPont de Nemours (Luxembourg) S.à r.l.
L-2984 Luxembourg
Tel: +352 3666 5779

www.typargeo.dupont.com

Style	Width (m)	Length (m)	Area (m ²)	Roll diameter (cm)	Roll weight (kg)	Maximum number of rolls per full truck (13.6 loading meters)	D Code
SF20	2.25	250	563	32	44	240	D13408146
	4.50	200	900	28	72	165	D13408602
	5.20	400	2080	38	154	70	D13541592
SF24	2.10	200	420	29	34	288	D14537652
	4.50	200	900	29	72	144	D14537633
	5.20	200	1040	29	83	96	D14537643
SF27	2.10	200	420	29	43	288	D13407663
	4.50	200	900	29	92	144	D13407762
	5.20	200	1040	29	107	96	D13407507
SF32	2.00	200	400	30	49	288	D13408024
	4.50	200	900	30	110	144	D13407516
	5.20	200	1040	30	127	96	D13407714
SF33	2.10	150	315	29	35	330	D14646161
	4.50	150	675	29	74	165	D14646189
	5.20	150	780	29	86	110	D14584751
SF37	2.10	150	315	29	45	330	D13407829
	4.50	150	675	29	96	165	D13407708
	5.20	150	780	29	111	110	D13407540
SF40	2.10	150	315	30	48	288	D13408047
	4.50	150	675	30	103	144	D13407983
	5.20	150	780	30	119	96	D13407475
SF44	4.50	150	675	31	113	144	D13539827
	5.20	150	780	31	130	96	D13408626
SF45	4.50	100	450	27	68	165	D14662697
	5.20	100	520	27	78	110	D14584767
SF49	4.50	100	450	26	86	165	D13407830
	5.20	100	520	26	99	110	D13407685
SF56	4.50	100	450	29	97	165	D13408204
	5.20	100	520	29	112	110	D13407679
SF65	4.50	100	450	30	110	144	D13408742
	5.20	100	520	30	127	96	D13407722
SF77	4.50	100	450	32	128	144	D13408712
	5.20	100	520	32	148	96	D13408212
SF85	4.50	100	450	33	142	144	D13540279
	5.20	100	520	33	164	96	D13540262
SF95	5.20	100	520	35	179	70	D15520072



Further product information is available upon request. This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own testing. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

DuPont de Nemours (Luxembourg) S.à r.l.
L-2984 Luxembourg
Tel: +352 3666 5779

www.typargeo.dupont.com